


RESPONSE TO NOTICE
U.S. Appln. No. 09/559,595

Page 6, please delete the fifth full paragraph, and replace it with the following new paragraph:

B2 The treated filler is then added to the organic compound, i.e. very low density polyethylene (VLDPE) at a concentration of 5% by weight. The mixture is then blended for 5 min at 160 °C, after which it is extruded or molded around the cable.

Respectfully submitted,


L. Raul Tamayo
Registration No. 47,125

SUGHRUE MION, PLLC
2100 Pennsylvania Avenue, N.W.
Washington, D.C. 20037-3213
Telephone: (202) 293-7060
Facsimile: (202) 293-7860

Date: April 9, 2002